

300 Gen Colin Powell Pkwy, Phenix City, AL 36869

Telephone: 1-800-554-7424 Fax: 334-664-3212

TexTesT Report: 1263549
Date: 10/11/13
Page: 1 of 1

CLIENT:

FIRE RETARDANT COATINGS OF TEXAS
1150 BLUE MOUND RD WEST # 202
HASLET, TX 76052

ATTN: DAVID PAULO

SAMPLE IDENTIFICATION:

STYLE: CANVAS-FX FABRIC GUARD
COLOR BLACK

<u>NFPA 701 (2010) TEST 1 FLAMMABILITY</u>		<u>Mass Before Test (grams)</u>	<u>Mass After Test (grams)</u>	<u>Mass Loss %</u>	<u>Drip Burn (Seconds)</u>	<u>After Flame (Seconds)</u>
SPECIMEN *	#1	29.0	27.1	6.59	0.0	0.0
	#2	28.4	26.4	7.18	0.0	0.0
	#3	29.0	27.4	5.25	0.0	0.0
	#4	28.6	27.5	4.16	0.0	0.0
	#5	28.6	25.3	11.50	0.0	0.0
	#6	28.0	25.8	7.79	0.0	0.0
	#7	28.3	26.2	7.36	0.0	0.0
	#8	28.1	23.5	16.42	0.0	0.0
	#9	28.2	25.4	9.72	0.0	0.0
	#10	27.8	24.5	<u>11.84</u>	<u>0.0</u>	0.0
	Average			8.78	0.0	
	Avg. + 3 Std. Dev.			19.74		

* Specimens were conditioned at least (30 minutes at 105±5°C) (24 hours at 20±5°C) before testing.

CRITERIA:

PASS/FAIL


MASS LOSS:

40% Max. Avg. or
Avg. + 3 Standard Deviations Max. Ind.

DRIP BURN:

2 Seconds Max. Avg.

COMMENTS:

The submitted sample passes the requirements of NFPA 701 (2010)
Test 1 Flammability.

Signed by