



LISTING REPORT

Number: **UEL-5019**

Originally Issued: 09/25/2018

Revised: 09/30/2020

Valid Through: 09/30/2021

LISTING REPORT FOR SURFACE BURNING CHARACTERISTICS

LISTING SUBJECT:

FX Lumber Guard and FX Lumber Guard XT Applied to Oriented Strand Board and Plywood

LISTEE:

**FIRE RETARDANT COATINGS OF TEXAS, LLC
1150 Blue Mound Road West, Suite 403
Haslet, Texas 76052
(817) 710-5233
www.frctexas.com**

CSI Section:

**09 96 43 Fire-Retardant Coatings
06 05 73.13 Fire-Retardant Wood Treatment**

1.0 SCOPE OF LISTING

1.1 Compliance with the following Standards:

- ASTM E84 – Standard Test Method for Surface Burning Characteristics of Building Materials
- ASTM E2768 – Standard Test Method for Extended Duration Surface Burning Characteristics of Building Materials (30 min Tunnel Test)

1.2 Properties assessed:

- Surface Burning Characteristics

2.0 FINDINGS

2.1 Product Information: FX Lumber Guard and Lumber Guard XT are clear, water-based liquid applied fire-retardant products. The products are supplied in 1 quart, 1 gallon and 5 gallons (0.95L, 3.78L, and 18.9L, respectively) containers with a shelf-life of 3-years when stored in sealed containers at temperatures between 45°F and 95°F (7.2°C to 35°C).

2.2 Surface Burning Characteristics: FX Lumber Guard and Lumber Guard XT, when applied at a coverage rated of 333 square feet per gallon to plywood and Oriented Strand Board, and tested in accordance with ASTM E84/ASTM E2768 extended 30-minute duration, exhibited a flame spread index of 25 or less. The flame front did not progress more than 10.5 ft. (3.2 m) beyond the centerline of the burners during the 30-minute exposure.


3.0 DESIGN AND INSTALLATION

3.1 General: FX Lumber Guard and Lumber Guard XT shall be applied in accordance with this listing and the FX

Lumber Guard and Lumber Guard XT published instructions, by applicators qualified by Fire Retardant Coatings of Texas. Copies of this listing and the Fire Retardant Coatings of Texas instructions shall be available at the jobsite. Where conflicts occur, the more restrictive shall govern. FX Lumber Guard and FX Lumber Guard XT are liquid applied by using rollers, brushes, or sprayers in one-coat to surfaces that are clean, dry, and free from dirt, grease, oil and prior coatings of paints, stains or sealers. The fire-retardant products shall be applied when the ambient temperature is between 45°F and 95°F (7.2°C and 35°C, respectively). At time of application the moisture content of dimensional lumber shall not exceed 15 percent and the moisture content of plywood shall not exceed 19 percent. The coatings are applied at a coverage rate of 300 to 350 square feet per gallon (7.36 to 8.59 m²/L). FX Lumber Guard and FX Lumber Guard XT have a cure time of between 8 and 32 hours depending on temperature and humidity.

4.0 IDENTIFICATION

Containers of FX Lumber Guard and FX Lumber Guard XT fire-retardant products are identified with the manufacturer's name (Fire Retardant Coatings of Texas, LLC), address, product name, manufactured date, shelf life, application instructions and listing report number (UEL-5019). Either Mark of Conformity may be used as shown below:



Brian Gerber

**Brian Gerber, P.E., S.E.
Vice President, Technical Operations
Uniform Evaluation Service**

Richard Beck

**Richard Beck, PE, CBO, MCP
Vice President, Uniform Evaluation Service**

Russ Chaney

**GP Russ Chaney
CEO, The IAPMO Group**

For additional information about this evaluation report please visit www.uniform-es.org or email us at info@uniform-es.org

